



West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Page 1 of 1

Client: Camira Fabrics Ltd
Meltham Mills
Meltham, HD9 4AY

Entry No: 43381

Date Received: 16th April 2010

Client's Description: Sample of fabric Xtreme Plus

TEST REPORT

Tests Required: Pilling

Conditioning: In accordance with BS EN ISO 139 : 2005 for a minimum of 24 hours at 65 +/- 4% Relative Humidity, 20 +/- 2°C

Method of Test: BS EN ISO 12945-2 : 2000

Date of Test: 23.4.10

The test was carried out using a load of 415 g

After 2,000 rubs:- 5
After 5,000 rubs:- 5

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



1104

G Briggs
Head of Laboratory
26th April 2010

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

