



West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Camira Fabrics
Hopton Mills
Mirfield
WF14 8HE

Entry No: 31762

Date Received: 20th November 2006

Client's Description: Sample of Fabric "Xtreme Plus"

TEST REPORT

Tests Required: All tests specified in Tables 1 & 2 of BS EN 14465

Date of Tests: 22.11.06 to 28.11.06

Conditioning: 24 hours at 65 +/- 4% Relative Humidity, 20 +/- 2°C where required

Abrasion: BS EN ISO 12947-2 : 1999

The tests were carried out using a pressure of 12 +/- 0.3 kPa.
The criterion for judging end point was three threads broken.
The test was terminated after 100,000 rubs without an end point having been reached.

Change in colour after 3,000 rubs 4-5

Observation Technique:- 10 fold magnification
Type of Fabric:- Flat Woven

Comments

On the basis of the tests carried out this sample of fabric has a Performance Level Category Rating A (over 35,000 rubs) as specified in Table 1 of BS EN 14465 : 20003. When compared with BS 2543 : 2004 this sample of fabric satisfies the requirements of fabrics for severe contract use.

----- End of Page -----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs
Head of Laboratory
30th November 2006

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



- * Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- * Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- * This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

